

페라이트자석 특성표

Grade	자속밀도(Br)		보자력 (Coercivforce) bHc		고유보자력 iHc		최대에너지적 (BH Max)	
	KG	KA/m	Koe	KA/m	KOe	Kj/m3	MGOe	KG
Y10T (C1)	11.7-12.1	1.77-12.1	10.8-11.5	860-915	12	955	33-35	263-279
Y25	11.9-12.2	1.19-1.22	11.0-11.4	876-907	12	955	34-36	271-287
Y30 (C5)	12.4-12.6	1.24-1.26	11.4-11.5	907-915	12	955	37-38	295-303
Y30BH	12.7-12.9	1.27-1.29	10.5-11.0	915-923	12	955	39-40	310-318
Y33	13.0-13.3	1.30-1.33	10.0-10.5	796-836	12	955	40-42	318-334
Y35	13.0-13.3	1.30-1.33	10.5-11.0	836-876	12	955	41-43	326-342
C8 (C8A)	13.3-13.7	1.33-1.37	10.5-11.0	836-876	12	965	43-45	358-342
C10	13.7-14.0	1.37-1.40	10.5-11.0	836-876	12	965	47-51	374-390